

# WDS<sup>®</sup> LambdaFlex<sup>®</sup> Super

## Product Data Sheet



### Product Description

WDS LambdaFlex Super is an encapsulated flexible and compact microporous insulation sheet specifically designed for applications requiring resistance to compression, together with low shrinkage and very low thermal conductivity up to their classification temperature.

Flexibility and water repellence are ensured by an outer encapsulation facing, constituted of a PE/Aluminum foil envelope which protects the microporous core.

Like any other microporous insulation of our industrial range produced with our exclusive WDS Technology process, this product features extremely good handling and cutting properties, low thermal conductivity coefficient giving it very good insulating properties in limited thickness allowing to design equipment where high energy efficiency and energy storage, space optimization and reduction of weight are premium factors to be considered.

### Features

- Flexible
- Large variety of format and sizes
- Excellent compressive strength
- Very low thermal conductivity in a wide temperature spectrum
- Not affected by thermal shock
- Non combustible
- Excellent handling properties
- Homogeneity throughout the entire surface and thickness of the blanket leading to consistency in performances per square area of material installed
- Water-repellent through encapsulation

### Benefits

- Dimensionally stable over time up to the maximum using temperature
- Helps to control energy efficiency and heat flow very precisely
- Easy to cut and with proven installation techniques
- Easy to install
- Adapt well on curved surfaces
- Increases effective volume inner capacity or reduces encumbrance in equipment of various kind
- Environmentally friendly

### Applications

- Back up insulation of transport and process ladles, torpedo ladles, tundishes.
- Back-up insulation of metal transfer systems
- Batteries
- Data recorder devices

### Environmental and Health Safety

WDS LambdaFlex Super does not contain any hazardous substance as defined by EU Directive 2006/1907/EEC and IARC. The fibers or filaments used as reinforcement of the mineral core are also exonerated from any classification falling under EU Directive 97/69/EC.

### Resistance to Moisture and Water

Thanks to an encapsulation process WDS LambdaFlex Super, is completely sealed tight therefore not affected by liquids; when cutting the material, it is good practice to re-seal the cut part with bi-adhesive aluminum tape to ensure no liquid infiltration could occur.

# WDS<sup>®</sup> LambdaFlex<sup>®</sup> Super

## Product Data Sheet



Properties		WDS LambdaFlex Super
Classification Temperature, °C (°F)		1050 (1922)
Density, kg/m <sup>3</sup> (pcf), nominal		415 (25.9)
Cold Compression Strength, MPa (psi), ASTM C 165		> 0.94 (136.2)
Linear Shrinkage, %, ASTM C 365		
Full soak, 1000°C (1832°F), 24 hours		<2.0
Single side soak, 1000°C (1832°F), 12 hours		<0.5
Chemical Analysis, %		
	Silica, SiO <sub>2</sub>	40-60
	Zirconium silicate ZrSiO	25-45
	Others	20-35
Thermal Conductivity, W/m·K (BTU·in/hr·ft <sup>2</sup> ·°F), ASTM C 177		
	200°C (392°F)	0.032 (0.222)
	400°C (752°F)	0.037 (0.257)
	600°C (1112°F)	0.045 (0.312)
	800°C (1472°F)	0.060 (0,416)

### Shelf Life

- WDS LambdaFlex Super sheets should be kept in dry conditions, not exposed to sunlight or source of heat and inside their original packaging.
- Although unlikely, loss of vacuum of the outer envelope may occur time to time in case the material is not properly stored.
- Should this occur, the properties of the product, notably thermal and mechanical performances overall, are not be affected.

### Standard Dimensions and Availability

Board Size, mm (in)	Thickness, mm (in)
1000 x 600 (39.3 x 23.6)	3, 5, 7, 10, 12 (0.12, 0.19, 0.27, 0.29, 0.47)
500 x 600 (19.5 x 23.6)	
500 x 500 (19.5 x 19.5)	
500 x 250 (19.5 x 9.7)	

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.